



Technical Data Sheet: 3DXSTAT™ ESD-TPU (95A) 3D Printing Filament

Physical Properties	Standard	Unit	Typical Value
Density	ISO 1183	g/cc	1.18

Material Properties	Standard	Unit	Typical Value
Tensile Strength, Yield	ISO 527	MPa	28
Tensile Elongation, Yield	ISO 527	%	>300
Flexural Strength	ISO 178	MPa	31
Abrasion Loss	ISO 4649-A	mm ³	25
Shore Hardness	ISO 7619	-	95A

Flamibility Rating	Standard	Unit	Typical Value
UL Flame Rating	UL94	-	HB

Electrical Property	Standard	Unit	Typical Value
Surface Resistance	ASTM D257	Ohm/sq	>10 ⁷ - 10 ⁹ <

Printed Specimen Conditions
Printer: Open Source FDM/FFF
Nozzle: 0.4mm
Layer Height: 0.25mm
Infill: 100%, +/- 45°
Extrusion Temp: 260°C
Bed Temp: 60°C
Specimen Orientation: XY Flat

www.3dxtech.com

Disclaimer: The technical data contained on this data sheet is furnished without charge or obligation and accepted at the recipient's sole risk. This data should not be used to establish specifications limits or used alone as the basis of design. The data provided is not intended to substitute any testing that may be required to determine fitness for any specific use.