



How to choose the right masking tape.

3M™ Color Masking Tapes make it easy to select the right tape for most applications. Asking a few simple questions up front should narrow choices down to one or two ideal tapes:

- How much heat will the tape be exposed to?
- How long will the tape be applied before removal?
- How much holding power does the job require—low, medium or high?
- How important is a razor-sharp paint edge?

Class 1 Masking

Crepe		Flatback	
Product Number		Product Number	
2	2693 up to 325°F	13	2525 up to 300°F
3	231 up to 300°F	14	2526 up to 300°F
4	232 up to 250°F		
5	233+ up to 250°F		
6	2750 up to 250°F		

Try the new ScotchBlue™!

Class 2 Masking

7	2380 up to 325°F	15	2517 up to 300°F
8	2364 up to 300°F	16	2460 up to 300°F
9	234 up to 250°F	17	2480S up to 200°F

NEW!

NEW!

Class 3 Masking

10	2307 up to 200°F	18	2515 up to 200°F
11	200 up to 200°F		
12	2214 up to 150°F		

Increasing holding power, line sharpness, clean removal time and temperature resistance >>

Increasing holding power, backing strength and temperature resistance >>



2750

ScotchBlue™ Industrial Masking Tape 2750

- Temperature resistance: up to 250°F
- Holding strength: high
- Clean removal: up to 3 days
- Superior UV and bleed-through resistance



2460

Scotch® Ultimate Paint Edge Masking Tape 2460

- Temperature resistance: up to 300°F
- Holding strength: low to medium
- Clean removal: better than traditional masking tapes
- Long, straight, sharp paint lines



2480S

Scotch® 60-Day Ultimate Paint Edge Masking Tape 2480S







- Temperature resistance: up to 200°F
- Holding strength: low to medium
- Clean removal: up to 60 days—even in the sun
- Razor-sharp paint edges

ScotchBlue™ 2080 and 2090 tapes are designed for use at room temperature.

NOTE: All temperatures are for a 30-minute bake.



3M™ Color Masking Tapes Attributes

3M™ Color Masking Tape	2750	2090	233+	2480S	2460	2080
ATTRIBUTES		 19				 20
Color	Blue	Blue	Green	Sea Green	Gold	Blue
Backing/Adhesive	Crepe/*NR	Crepe/Acrylic	Crepe/*NR	Flatback/Acrylic	Flatback/Acrylic	Flatback/Acrylic
Holding strength to common surfaces (i.e. steel, paints):						
Low				Recommended	Recommended	Recommended
Medium		Recommended				
High	Recommended		Recommended			
Hold to and remove cleanly from specialty surfaces:						
Stainless steel	Recommended	Recommended	Recommended	Recommended	Recommended	Recommended
EPDM rubber	Recommended	Recommended	Recommended	Recommended	Recommended	Recommended
Paint compatibility	Latex and Solvent (including ketone-based paints)	Latex (not ketone-based paints)	Latex and Solvent (including ketone-based paints)	Latex and Solvent (including ketone-based paints)	Latex and Solvent (including ketone-based paints)	Latex and Solvent (not ketone-based paints)
Recommended Max Bake Temperature	250°F	Room Temp	250°F	200°F	300°F	Room Temp
Adhesion to Steel oz./in. width	38	25	36	13	9	12
Tensile Strength lbs./in. width	27	27	25	18	17	19
Elongation at Break (%)	8	6.7	10	6	5	6
Tape Thickness (mils)	6.3	5.4	6.7	4.0	3.3	3.8
Clean Removal on Opaque Surfaces: Up to __ Days	3	14	3	60	TBD	60

*NR = Natural Rubber



Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
1-800-362-3550
www.3M.com/colormaskingtapes
www.3M.com/industrialtapes

3M, ScotchBlue, the BLUE color of the tape and the Plaid Design are trademarks of 3M Company. Scotch is a registered trademark of 3M Company. Please recycle. Printed in USA. © 2010, 2011, 3M. All rights reserved. 70-0711-0230-8 (Rev A)

TECHNICAL INFORMATION: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

WARRANTY, LIMITED REMEDY, AND DISCLAIMER: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

LIMITATION OF LIABILITY: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.