




Daylight Magna Durable

SPECS



KEY FEATURES

Photocentric's Daylight Magna Durable formulation is ideal for 3D-printing functional parts that are durable and long-lasting, with high impact strength that can also bend without breaking. Thick objects are stiff but can be made to flex under strain, while returning to their original shape.

With excellent imaging in the LC Magna, this resin has fast exposure times and a wide exposure latitude. Allowing the parts to also hold the finest details possible from LC Magna. The finished material is tough, durable and long lasting provided it is stored in dry conditions away from strong UV light.

PRINTING (PROCESSING) INSTRUCTIONS

Follow the procedures laid out in the LC Magna user manual. Shake resin prior to use, recommended 2 minutes. Avoid direct sunlight while pouring. The resin is reusable after pouring through the supplied filter and funnel to remove any solids. Always keep door closed when not in use to avoid curing or contamination.

Post Processing guidelines:

- Do not leave the platform in the ambient light before washing and post exposing, this may lead to liquid resin curing.
- Wash in the Wash 99L for a maximum of 15 minutes.
- Rinse with hot water to remove residue cleaner and resin
- Dry with air compressor to remove any remaining water.
- Post cure in a pre-heated Cure L for 2 hours at 60 degrees, for larger parts it can take up to 4 hours to post cure.

Support guidelines:

- Support profile for small parts – 0.4mm tips / 1.5mm pole diameter / 2mm widening factor
- Support profile for large parts – 0.6mm tips / 2mm pole diameter / 2mm widening factor

Recommended resin temperature (pre-printing)

- 30°C

DATA

Viscosity <small>(At 25°C Brookfield spindle 3)</small>	1200 cPs
Hardness <small>ASTM D2240 (After post exposure for 60 minutes at 60°C)</small>	60 Shore D
Tensile strength <small>ASTM D638 (After post exposure for 60 minutes at 60°C)</small>	42 MPa
Elongation at break <small>ASTM D638 (After post exposure)</small>	14%
Young's modulus <small>ASTM D638 (After post exposure for 60 minutes at 60°C)</small>	1570 MPa
Impact strength notched Izod <small>ASTM D256 (After post exposure)</small>	14 kJ/m2
Flexural strength <small>ASTM D792 (After post exposure)</small>	28 MPa
Flexural modulus <small>ASTM D792 (After post exposure)</small>	760 MPa
Water absorption (24 h at 60°C)	0.9 wt%
Heat deflection temperature	75°C
Storage	10<t>50°C
Density	1.09 g/cm3

AVAILABLE COLOURS

Black.

Available in 5kg bottles.

