

## Neutral Cure Silicone Adhesive Sealant (Black) 20g Squeeze Tube

### Product Highlights

Neutral Cure RTV Silicone  
Bonds to a Wider Variety of Substances  
Seals, Bonds, Encapsulates  
Resistant to Various Chemicals and Oils  
Non-Corrosive, Non-Conductive  
Flexible, Durable, Non-Degrading  
Withstands Moisture, Vibration, Abrasion



### Common Uses

Protecting, Sealing and Insulating.  
Bonding to Aluminum, Vinyl, Fiberglass, Ceramics, Brick, Mortar, Concrete, Glass, Granite, Marble, Metals, Wood, Plastic, Porcelain, PVC, Steel.  
OEM Commercial and Industrial Manufacturing for Flexible Permanent Bonding and Sealing.

### Instructions

Surfaces should be clean and dry. Unscrew cap, cut the tip off. If tooling is required, do so within the first 10 minutes after dispensing. Apply the silicone to surfaces and remove the excess silicone after tooling with a dry clean cloth. Allow the silicone to cure completely. At room temperature, 25°C (77°F), and 50% relative humidity, the silicone will skin in 10 minutes and fully cure in 24 hours (1/8" bead). The silicone will reach its maximum adhesion in 7 days. Higher humidity accelerates curing.

### Specifications

Meets and Exceeds:	ASTM C920, TT-S-00230C, TT-S-001543A, MIL-46106 Type 1
VOC:	VOC Compliant (<3%), Low Odor
Operating Temperature Range:	-57°C to +204°C (-70°F to +400°F)
Curing Time:	10 min (skin), 24 hours (full cure), 7 days (max adhesion)
Color:	Black
Size:	20g squeeze tube
Shore A Hardness:	30
Tensile Strength:	250psi
Tear Strength:	30psi
Elongation:	400%
Dielectric Strength:	460 V/mil (18 kV/mm)

### Storage and Handling

Store refrigerated or at room temperature 3-25°C (37-77°F).

### Shelf Life

>36 months

### Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.