

Super Glue - Thin Viscosity - Penetrating 0.5oz

Product Highlights

Thin viscosity penetrating super glue.

Use for penetrating tight fitting joints.

Bonds: Metal, Plastic, Wood, Cardboard, Paper, Ceramic, Leather and More!

Specifications

Viscosity:	5 cP (5 mPas)
Curing Time:	3 seconds
Main Ingredient:	Cyanoacrylate
Thermal Conductivity (after curing):	0.2 W/mK
Operating Temperature (after curing):	-30°C to 90°C (-22°F to 194°F)
Size:	15ml Squeeze Bottle



Storage and Handling

Store at 3-25°C (37-77°F). Do not freeze. Allow 4 hours for thermoset chip glue to reach an operating temperature of 20-25°C (68-77°F) before use.

Shelf Life

>24 months (unopened)

Transportation

This product has no shipping restrictions, when total shipment volume of Super Glue does not exceed 1000ml (qty 66 of 15ml bottles). Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.

Chip Quik Super Glue Available Part Numbers

Orderable Part Number	Viscosity	Curing Time	Main Ingredient	Thermal Conductivity	Operating Temperature	Size
SG1-0.5	5cP	3 seconds	Cyanocrylate	0.2 W/mK	-30°C to 90°C (-22°F to 194°F)	15 ml
SG1-1.0	5cP	3 seconds	Cyanocrylate	0.2 W/mK	-30°C to 90°C (-22°F to 194°F)	30 ml
SG2-0.5	100 cP	15 seconds	Cyanocrylate	0.2W/mK	-30°C to 90°C (-22°F to 194°F)	15 ml
SG2-1.0	100 cP	15 seconds	Cyanocrylate	0.2W/mK	-30°C to 90°C (-22°F to 194°F)	30 ml
SG3-0.5	700 cP	45 seconds	Cyanocrylate	0.2 W/mK	-30°C to 90°C (-22°F to 194°F)	15 ml
SG3-1.0	700 cP	45 seconds	Cyanocrylate	0.2 W/mK	-30°C to 90°C (-22°F to 194°F)	30 ml
SG4-1.0	700 cP	45 seconds	Cyanocrylate	0.2W/mK	-30°C to 90°C (-22°F to 194°F)	30 ml