




HFT5000

Heat-shrinkable fabric tubing

Polyester Warp (longitudinal member non-shrinkable)



- Heat-shrinkable fabric tubing
- Highly flexible woven fabric tubing
- Polyethylene/polyester construction for excellent abrasion resistance
- Low shrink temperature
- Halogen free
- 2:1 shrink ratio

Raychem HFT5000 products are made of very flexible heat-shrinkable fabric material. Heated above 100°C, they shrink and fit snugly and securely around the underlying substrate. Designed primarily to provide mechanical abrasion protection for components such as rubber hoses, plastic pipes, and harness wiring bundles, they are also suitable for other applications, such as noise and rattle suppression.

Woven from heat-shrinkable circumferential polyolefin filaments and non-shrinking longitudinal polyester fibres, the product is halogen free. The woven construction makes HFT5000 extremely flexible and resistant to trapping water, heat and humidity. It provides outstanding abrasion, chafing and cutting protection, even at high temperatures. HFT5000 product is easy to install and can be cut with standard industrial cutting equipment.


Tyco, Raychem and HFT are trademarks. Other products, logos, company names mentioned herein may be trademarks of other respective owners.

All of the above material, including illustrations, is believed to be reliable. Users, however should independently evaluate the suitability of each product for their application. Tyco Electronics makes no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. Tyco Electronics only obligations are those in the Standard Terms and Conditions of Sale for this product and in no case will Tyco Flectronics be liable for any incidental indirect or consequential damages arising from the sale, resale, use or misuse of the product. Tyco Electronics Specifications are subject to change without notice. In addition Tyco Electronics reserves the right to make changes in materials or processing without notification to the Buyer, which do not affect compliance with any applicable specification.

Ordering information

Standard sizes

Inside diameter (mm/in)



Standard colours	Colour	Black	Note: Fully recoverable fabric wall thickness: Approximately 1 mm (0.039in). Longitudinal change on full recovery is —
	Code	0	
	Standard packaging	1 spool per box	10% to -20%
	•	•	- 0 = Black

Test	Test method	Test requirement
Thermal ageing:	3000 hrs at 125°C	No deterioration in abrasion
		resistance at 80°C
	1000 hrs at 150°C	No deterioration in abrasion
		resistance at 80°C
Flammability:	MVSS302	Pass
Low temperature	4 hours at -40°C,	No cracking
flexibility:	10X diameter mandrel	
Cold impact:	200g weight from 100mm at -40°C	No cracking
Temperature/	See RW2060 for details	No deterioration in abrasion
humidity cycling:		resistance at 80°C
Thermal shock:	100 cycles between	No deterioration in abrasion
	-40°C and 125°C	resistance at 80°C
Fluid resistance:	24 hr immersion at 23°C	No deterioration in abrasion
		resistance at 80°C
	Test fluids:	Antifreeze (50% ethylene glycol)
	(24hr immersion at 23°C)	Engine oil (SAE 10W/30)
		Mineral hydraulic fluid
		Detergent (1% Teepol)
		Brake fluid (DOT 4)
		Unleaded gasoline
		Diesel fuel
		Battery acid (1.25 SG H ₂ SO ₄)
	Flammability: Low temperature flexibility: Cold impact: Temperature/ humidity cycling: Thermal shock:	Flammability: MVSS302 Low temperature flexibility: Cold impact: Temperature/ humidity cycling: Thermal shock: MVSS302 4 hours at -40°C, 10X diameter mandrel 200gweightfrom 100mmat -40°C See RW2060 for details 100 cycles between -40°C and 125°C Fluid resistance: 24 hr immersion at 23°C Test fluids:

For full product performance details consult Raychem Specification RW 2060.

Specifications	Raychem	Specification	RW 2060

Material Safety Data Sheet available on request.

Installation instructions available on request.







