



- **Rated to 155°C Class F**
- **UL Recognized File# E329693**
- **Grade A (7,000 V)**
- **Grade C (2,500 V)**
- **Cut and Abrasion Resistant**
- **Excellent Low Temp. Flexibility -13°F**
- **Resists Acids and Most Organic Solvents**

Acrylic Resin Coated Fiberglass Sleeving Grade A & C

ACRYLIC FLEX GLASS (AG) sleeving is a heat-treated, tightly braided fiberglass sleeving coated with a dielectric acrylic resin. This durable sleeving will withstand mechanical stress and holds it's dielectric strength on all bends.

Acrylic Flex Glass is used in applications such as relays, radio circuits, transformers, and lead/crossover protection on motors. Highly resistant to acids and solvents, and will withstand tough assembly handling. Sleeving is recommended for thermal requirements from 105°C (221°F) to 155°C (311°F) ranges.



Cut Cleanly
Scissors

Acrylic Resin Coated Flex Glass sleeving has superior mechanical and electrical properties, providing its rated dielectric strength during and after the most severe handling in your application.

Colors Available:
4= YL, NT, BK, & RD.



Material
Acrylic Coated Fiberglass

Grade
A & C

Wall Thickness
.014" - .040"

Colors Available:



Yellow (YL), Natural (NT), Black (BK) and Red (RD).



800.323.5140 • 973.300.9242 • fax: 973.300.9409
104 Demarest Road • Sparta, NJ 07871





Put-Ups

Nominal Size	Diameter	Part#	Grade	Wall Thickness (Grade A)	Part#	Grade	Wall Thickness (Grade C)	Bulk Spool	Shop Spool	Available Colors
24	0.022"	AGAG.24	A	.018"	AGCG.24	C	.014"	500'	250'	YL,NT,BK,RD
22	0.027"	AGAG.22	A	.018"	AGCG.22	C	.014"	500'	250'	YL,NT,BK,RD
20	0.034"	AGAG.20	A	.018"	AGCG.20	C	.014"	500'	250'	YL,NT,BK,RD
18	0.042"	AGAG.18	A	.018"	AGCG.18	C	.014"	500'	250'	YL,NT,BK,RD
16	0.053"	AGAG.16	A	.020"	AGCG.16	C	.016"	500'	250'	YL,NT,BK,RD
14	0.066"	AGAG.14	A	.020"	AGCG.14	C	.016"	500'	250'	YL,NT,BK,RD
12	0.085"	AGAG.12	A	.022"	AGCG.12	C	.017"	250'	100'	YL,NT,BK,RD
11	0.095"	AGAG.11	A	.022"	AGCG.11	C	.017"	250'	100'	YL,NT,BK,RD
10	0.106"	AGAG.10	A	.022"	AGCG.10	C	.017"	250'	100'	YL,NT,BK,RD
9	0.118"	AGAG.09	A	.024"	AGCG.09	C	.019"	250'	100'	YL,NT,BK,RD
8	0.133"	AGAG.08	A	.024"	AGCG.08	C	.019"	250'	100'	YL,NT,BK,RD
7	0.148"	AGAG.07	A	.024"	AGCG.07	C	.019"	250'	100'	YL,NT,BK,RD
6	0.166"	AGAG.06	A	.024"	AGCG.06	C	.019"	250'	100'	YL,NT,BK,RD
5	0.186"	AGAG.05	A	.028"	AGCG.05	C	.023"	250'	100'	YL,NT,BK,RD
4	0.208"	AGAG.04	A	.028"	AGCG.04	C	.023"	250'	100'	YL,NT,BK,RD
3	0.234"	AGAG.03	A	.028"	AGCG.03	C	.023"	250'	100'	YL,NT,BK,RD
2	0.263"	AGAG.02	A	.028"	AGCG.02	C	.023"	250'	100'	YL,NT,BK,RD
1	0.294"	AGAG.01	A	.028"	AGCG.01	C	.023"	100'	50'	YL,NT,BK,RD
0	0.330"	AGAG.00	A	.028"	AGCG.00	C	.023"	100'	50'	YL,NT,BK,RD
3/8"	0.375"	AGA0.38	A	.034"	AGC0.38	C	.030"	100'	50'	YL,NT,BK,RD
7/16"	0.438"	AGA0.44	A	.034"	AGC0.44	C	.030"	100'	50'	YL,NT,BK,RD
1/2"	0.500"	AGA0.50	A	.034"	AGC0.50	C	.030"	100'	50'	YL,NT,BK,RD
5/8"	0.625"	AGA0.63	A	.034"	AGC0.63	C	.030"	100'	50'	YL,NT,BK,RD
3/4"	0.750"	AGA0.75	A	.040"	AGC0.75	C	.038"	100'	50'	YL,NT,BK,RD
7/8"	0.875"	AGA0.88	A	.040"	AGC0.88	C	.038"	100'	50'	YL,NT,BK,RD
1"	1.000"	AGA1.00	A	.040"	AGC1.00	C	.038"	100'	50'	YL,NT,BK,RD

www.techflex.com

RATE OF BURNING

Conforms with requirements of NEMA TF-1, MIL-I-003190/3, and ASTM D372.

CHEMICAL RESISTANCE

Resistant to oils, acids, alkalis and most organic solvents. After more than 168 hours in the most commonly used aromatics, xylene and toluene, the dried sleeving substantially regains its original properties.

LOW TEMPERATURE

Bends without cracking at -25°C/-13°F.

© 2020 Techflex® - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex® is strictly forbidden.

Techflex® product names and logos are registered trademarks of Techflex®, unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex® makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's® only obligations are those in standard terms of sale for these products and Techflex® will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications.